

SUNLITE®

Multi-Wall Polycarbonate Sheet



Glazing



Construction



DIY



Advertising



Agriculture

► Introduction

SUNLITE sheets combine the characteristic strength of polycarbonate with superior insulation. This combination yields a strong, insulating, lightweight and attractive sheet for varied roofing, cladding, and glazing. SUNLITE provides solutions for markets as diverse as construction, agriculture, industry, DIY and advertising.

► Features at a Glance

- **New:** X-Lite structure for improved overall mechanical performance
- Energy saving
- Excellent impact resistance
- Lightweight
- High light transmission
- Weather and UV resistant benefits
- Superb thermal insulation - Energy saving
- Blocks virtually all UV radiation
- Easy to handle and install
- High fire performance rating

► Applications

- Conservatories
- Skylights
- Signs
- Covered Walkways
- Industrial Roofing and Glazing
- Do-It-Yourself (DIY)
- Swimming Pools
- Greenhouses



Property	(Method)	Conditions	Units	Value
Density	(D-1505)		g/cm ³	1.2
Heat Deflection Temperature	(D-648)		°C	130
Service Temperature - Short Term			°C	-50 to +120
Service Temperature - Long Term			°C	-50 to +100
Coefficient of Linear Thermal Expansion	(D-696)		10 ⁻³ /°C	6.5
Tensile Strength at Yield	(D-638)		MPa	62
Elongation at Break	(D-638)		%	>80
Impact Falling Dart	(ISO 6603/1)		J	40 - 400
Theoretical Thermal Coefficient of Expansion			mm/m	3

Additional SUNLITE® Products

Structure	% Light Transmission by Colours										
	Standard Colours							Multi-Layer		New DC	
	Clear	Bronze	Solar Grey	White Opal	Opal WD	Solar Metallic Grey	Solar Ice	Bronze/Opal	Solar Guard	CL	AG
Twin Wall 4 mm	82%	35%	25%	30%		30%					
Twin Wall 4.5 mm	82%	35%	25%	30%		30%					
Twin Wall 6 mm	80%	35%	25%	20%		30%					
Twin Wall 8 mm	80%	35%	25%	35%		25%				45%	45%
Twin Wall 10 mm	79%	35%	25%	30%		25%				45%	45%
Triple Wall 8 mm	76%	35%		48%		25%					
Triple Wall 10 mm	76%	35%		48%		25%					
Triple Wall 16 mm	76%	35%	25%		48%	25%		20%	10%		
X-Lite 10 mm	63%										
X-Lite 16 mm	60%	25%			38%	18%	15%				30%
X-Lite 25 mm	60%	25%			20%	20%	15%	10%	5%		20%
X-Lite 32 mm	58%	20%			20%	20%	15%	10%	5%		20%
X-Lite 35 mm	57%	20%			20%	20%	15%	10%	5%		20%

Standard Dimensions

Structure	Thickness mm	Area Weight kg/m ²	U-value W/m ² °K	Standard Sheet Width (mm)							
				980	1050	1250	1600	1800	1830	2100	
Twin-Wall 	4	0.8	3.8	✓	✓	✓	✓			✓	✓
	4.5	1.0	3.7	✓	✓	✓	✓			✓	✓
	6	1.3	3.5	✓	✓	✓	✓			✓	✓
	8	1.5	3.3	✓	✓	✓	✓			✓	✓
	10	1.7	3.0	✓	✓	✓	✓			✓	✓
Triple-Wall 	8	1.7	2.9							✓	✓
	10	2.0	2.7							✓	✓
	16	2.7	2.3	✓	✓	✓	✓	✓	✓	✓	✓
X-Lite 	10	1.9	2.6							✓	✓
	16	2.5	2.1	✓	✓	✓	✓	✓	✓	✓	✓
	25	3.4	1.7	✓	✓	✓	✓	✓	✓	✓	✓
	32	3.7	1.6	✓	✓	✓	✓	✓	✓	✓	✓
	35	3.9	1.5	✓	✓	✓	✓	✓	✓	✓	✓

Flammability

SUNLITE complies with international fire resistance standards, as presented by the results in the following table :

Method	Classification*
BS 476/7	Class 1
DIN 4102	B-1
NSP 92501	M-1, M-2
ASTM D-635	CC-1 (SUNLITE® SL)
ASTM E-84	Class A

* For additional information please consult your SUNLITE distributor.

Colors

Standard
Clear, Bronze, Opal, Solar Metallic.

Special Transparent
Sky Blue, Sea Green.

ML (Multi-Layered)
Bronze/Opal, Solar Guard.

- Solar Control™** Breaking the penetrating heat/light ratio
- SUNLITE® UV2** UV protection on two sides
- SUNLITE® Plus** Clear SUNLITE with anti-condensation treatment
- SUNLITE® CL** With advanced heat filtering for architectural applications
- SUNLITE® AG** With special coloring and anti-condensation

Inasmuch as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.

